

# TEST REPORT

NO.: ASZ09092505001

Date: Sep 29, 2009

Page 1 of 3

**Customer:** Pepperell Crafts of Ningbo

**Address:** 1<sup>st</sup> Fangxin road, Fangqiao Industrial Zone, Jiangkou Street ,Fenghua, Ningbo, China

**Report on the submitted sample said to be:**

**Sample name:** BRASS RINGS

**Model:** R8M

**Item/Lot No.:** /

**Material:** /

**Buyer:** PEPPERELL BRAIDING COMPANY

**Supplier:** PEPPERELL CRAFTS OF NINGBO

**Manufacturer:** PEPPERELL CRAFTS OF NINGBO

**Sample received date:** Sep 25, 2009

**Testing period:** From Sep 25, 2009 to Sep 29, 2009

**Testing Requested:**

As specified by client, to determine the Lead content in the submitted sample in accordance with Consumer Product Safety Improvement Act of 2008 (H.R. 4040) section 101--Prohibition on sale of certain products containing lead.

**Test method:**

Testing Item	Test Method	Measuring instrument
Lead (Pb)	EPA 3052	ICP-OES

**Conclusion:** The submitted sample complied with the requirement.

\*\*\*\*\*FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)\*\*\*\*\*

Written by : Herry

Inspected by: Wally

Approved by: Jeanah

# TEST REPORT


NO.: ASZ09092505001

Date: Sep 29, 2009


Page 2 of 3

**Test Flow:**

To Determine Lead Content:



To Determine Lead Content(for plating layer):



**Test Results:**

Total lead content in substrate material :

Element	Unit	MQL	Limit	A	B
Total lead	mg/kg	5	300#	21.1	N.D.

**Note:**

- # The limit is 300ppm, after Aug 14, 2009
- The limit is 100ppm, after Aug 14, 2011

**Specimen Description:**

- A: Metal body
- B: Plating coat

**Note:**

- Specimens, which requested to determine Lead Content, have been dissolved completely.
- mg/kg = ppm
- N.D. =Not Detected (<MQL)
- MQL=Method Quantitation Limit
- Photo is included.


# TEST REPORT

NO.: ASZ09092505001

Date: Sep 29, 2009

Page 3 of 3

## Photograph of Sample



BRASS RINGS

\*\*\*End of Report\*\*\*